

# PRODUCT INFORMATION



## Kao Industrial (Thailand) Co., Ltd.

55 Wave Place Bldg. 14<sup>th</sup> & 15<sup>th</sup> Floor Wireless Road, Pathumwan , Bangkok, THAILAND (Zip: 10330)

Tel: +66-2-655-4433 / Fax: +66-2-655-4333

### Ca-Type Naphthalene Sulfonate Polymer

## MIGHTY 150CA

#### PRODUCT INFORMATION

Type of admixture	-	Dispersing agent
Chemical base	-	Calcium Type Naphthalene Sulfonate Dispersant
Appearance / Color	-	Dark brown liquid
Shelf life	-	12months from the date of production with unopened. Store under roof to prevent increase temperature to more than 30°C.
Density (30°C)	-	1.180-1.220
pH (5% aq.)	-	6.0-8.0
Package	-	Steel drum 200L , 1000kg container

#### USAGE

MIGHTY 150CA dosage rate can used in the range of 600 -2000 cc. per 100 kg. of gypsum or cement depending on requirement of water reduction, Quality of gypsum, W/G; Temperature and others concerning. it is advisable to conduct trial mixes to get the exact dosage rate.

#### PRECAUTIONARY INSTRUCTIONS

As it is normal with chemical admixtures for concrete and gypsum, the performance of MIGHTY 150CA may vary depending on the materials. Therefore, we suggest that the users run a prior testing with actual condition to determine the applicable rates of dosage.

For your safety, refer Safety Data Sheet before using. Anyone who intends to use this product, please wears protective equipment such as safety goggles, groove, mask and so on. Be careful not to put it in eyes. Wash off immediately with clean water in case of it getting eyes. After that, please go to an eye doctor. Drinking much water and throw up in case of swallowing it. After that, please get any medical treatment from a doctor. Wash hand and face after use it.

#### Kao Construction Business Group in ASIA

JAPAN	CHINA	TAIWAN	THAILAND	SINGAPORE	INDONESIA
Kao corporation	Kao Chemical Corporation	Kao (Taiwan) Corporation	Kao Industrial (Thailand) Co., Ltd.	Kao (Singapore) Private Ltd.	PT Kao Indonesia Chemicals
+81-3-5630-7641	+86-21-6409-2880	+886-2-8665-1978	+66-2-655-4433	+65-6298-8184	+66-2-655-4433